

# Stainless Steel – EN Standards for Cold Rolled

The old BS1449 standard has been replaced by two EN Standards:

Standard	Scope
EN10088-2	Replaces BS1449-Part 2: 1983
EN10059	Cover Heat Resisting Grades
EN10259	Tolerances for COLD Rolled material

For those familiar with the old BS standard it is useful to highlight where the new EN standards differ:

- ◆ 27 grades in BS have been replaced by 68 grades in EN and thus many EN grades do not have an old BS equivalent
- ◆ Mechanical Properties have been changed
- ◆ Tensile strengths are now higher and a maximum is stipulated
- ◆ Chemical Compositions vary slightly with Nickel contents being slightly lower
- ◆ 304S15, 304S16 & 304S31 have all been replaced by 1.4301
- ◆ EN 10088-2 states that Class A thickness tolerances shall normally be produced
- ◆ Surface Finish Standards have been extended and some changed

## Material Certification

Where multi-certification is required, a combination of EN10088-2, EN10029 or 10051 will appear together with the appropriate ASTM Standards.

## Flatness Tolerances

Nominal Length (L) (mm)	Normal Tolerance (mm)
Up to 3000	10
Over 32000	12

## Length Tolerances

Nominal Length (L) (mm)	Normal Tolerance (mm)
Up to 2000	+5 / -0
Over 2000	+0.0025 X L / -0

## Thickness Tolerances – EN10259

Thickness	Tolerance in mm (+ or -) for given width in mm		
	1000	1250	1500
Under 0,30	0.03	-	-
0.30 to 0.49	0.04	0.04	-
0.50 to 0.59	0.045	0.05	-
0.6 to 0.79	0.05	0.05	-
0.8 to 0.99	0.055	0.06	0.06
1,0 to 1.19	0.06	0.07	0.07
1.2 to 1.49	0.07	0.08	0/08
1.5 to 1.99	0.08	0.09	0.10
2.0 to 2.49	0.09	0.10	0.11
2.5 to 2,.99	0.11	0.12	0.12
3.0 to 3.99	0.13	0.14	0.14



*Amari is a registered trademark of Amari Metals Ltd*

© Copyright: Amari Metals Ltd, 25 High Street, Cobham, Surrey, KT11 3DH

All Data is indicative only and must not be seen as a substitute for the full specification from which it is drawn. In particular, the mechanical property requirements vary widely with temper, product form and product dimensions. For more complete details please refer to the relevant specification.

# Stainless Steel – EN Standards for Cold Rolled

## Width Tolerances

Thickness (mm)	All Plus Tolerance in mm for given width in mm (i.e. – 0)	
	1000	1250 & 1500
Under 1.5	+ 1.5	+ 2.0
1.5 to 2.49	+ 2.0	+ 2.5
2.5 to 3.49	+ 3.0	+ 3.0
3.5 and over	+ 4.0	+ 4.0

## Comparative Grades

AUSTENITIC				FERRITIC/MARTENSITIC	
BS 1449-2	EN 10088-2	BS 1449-2	EN 10088-2	BS 1449-2	EN 10088-2
284S16	-	316S13	1.4432	403S17	1.4000
301S21	1.4310	316S31	1.4401	405S17	1.4002
304S11	1.4307	316S33	1.4436	409S19	1.4512
304S15	1.4301	317S12	1.4438	430S17	1.4016
304S16	1.4301	317S16	-	434S17	1.4016
304S31	1.4301	320S31	1.4571	410S31	1.4006
305S19	1.4303	320S33	-	420S45	1.4028
315S16	-	321S31	1.4541		
316S11	1.4404	347S31	1.4550		

**N.B. The grades stated are the nearest comparisons and not direct equivalents.**

## Main Grade Differences

Grade	Carbon (%)		Chrome (%)		Nickel (%)		UTS (N/mm <sup>2</sup> )	
	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.
304S15	-	0.06	17.5	19.0	8.0	11.0	500	-
304S16	-	0.06	17.5	19.0	9.0	11.0	500	-
304S31	-	0.07	17.0	19.0	8.0	11.0	490	690
1.4301	-	0.07	17.0	19.5	8.0	10.5	540*	750*
304S11	-	0.03	17.0	19.0	9.0	12.0	480	-
1.4307	-	0.03	17.5	19.5	8.0	10.0	520*	670*
316S31	-	0.07	16.5	18.5	10.5	13.5	510	-
1.4401	-	0.07	16.5	18.5	10.0	13.0	530*	680*
316S11	-	0.03	16.5	18.5	11.0	14.0	490	-
1.4404	-	0.03	16.5	18.5	10.0	13.0	530*	680*

\* Tensile properties stated apply to steels in the solution annealed condition.



Amari is a registered trademark of Amari Metals Ltd

© Copyright: Amari Metals Ltd, 25 High Street, Cobham, Surrey, KT11 3DH

All Data is indicative only and must not be seen as a substitute for the full specification from which it is drawn. In particular, the mechanical property requirements vary widely with temper, product form and product dimensions. For more complete details please refer to the relevant specification.

# Stainless Steel – EN Standards for Cold Rolled

## Finishes according to BS EN 10088-2 / 10028-7

BS EN Finish	Old BS Finish	Description		
<b>Hot Rolled</b>				
1C	0	Hot rolled, heat treated, not descaled		
1E	1	Hot rolled, heat treated, mechanically descaled		
1D	1	Hot rolled, heat treated, pickled		
1U	-	Hot rolled, not heat treated, not descaled		
<b>Cold Rolled</b>				
2C	-	Cold rolled, heat treated, not descaled		
2E	-	Cold rolled, heat treated, mechanically descaled		
2D	2D	Cold rolled, heat treated, pickled		
2B	2B	Cold rolled, heat treated, pickled, skin passed		
2R	2A / (BA)	Cold rolled, bright annealed		
2Q	-	Cold rolled, hardened and tempered, scale-free		
<b>Special Finishes*</b>				
BS EN Finish	Old BS Finish	Description	Typical Grit	Typical R <sub>a</sub>
1G or 2G	-	Ground Grit	120	2.5 to 2.0 μ
1J or 2J	3B	Brushed - Unidirectional	180	1.2 to 1.0 μ
1J or 2J	4	Dull Polished – Unidirectional	240	0.6 μ
1K or 2K	5	Satin polished – Unidirectional	320	0.5 Max
1P or 2P	7	Bright polished – Non-Directional with a high degree of image clarity	600	0.1 μ
1P or 2P	8	Mirror Finish – Non-Directional with a very high degree of image clarity	800	0.05 μ
1M or 2M	-	Patterned		
2L	-	Coloured		
2W	-	Corrugated		
1S or 2S	-	Surface Coated (Metallic coatings such as tin, lead or aluminium)		
<p><b>*Note:</b> Special finishes indicate hot rolled (1) and cold rolled (2) sheets, e.g.:            Ground polished hot rolled sheets = 1G / Ground polished cold rolled sheets = 2G</p>				

**For more information on stainless steel finishes please refer to the datasheet on this subject.**



Amari is a registered trademark of Amari Metals Ltd

© Copyright: Amari Metals Ltd, 25 High Street, Cobham, Surrey, KT11 3DH

All Data is indicative only and must not be seen as a substitute for the full specification from which it is drawn. In particular, the mechanical property requirements vary widely with temper, product form and product dimensions. For more complete details please refer to the relevant specification.

# Stainless Steel – EN Standards for Cold Rolled

## Stainless Steel Grades, Compositions & Typical Mechanical Properties

EN	BS	AISI	EN No.	Composition Guide					Typical Mechanical Properties (Rolled Products)		
				Obsolete	C	Cr	Ni	Mo	Others	Proof Strength 0.2% Nmm <sub>2</sub>	Tensile Strength Nmm <sub>2</sub>
1.4000	403S17	410S	–	0.08x	12	.	.	.	220-250	400-600	19
1.4002	405S17	405	–	0.08x	12	.	.	0.2 Al	210-250	400-600	17
1.4003	–	–	–	0.03x	11	0.5	.	.	250-320	450-650	18-20
1.4016	430S17	430	60	0.08x	17	.	.	.	240-280	430-630	18-20
1.4113	434S17	434	–	0.08x	17	.	1	.	260-280	450-630	18
1.4509	–	–	–	0.015x	18	.	.	Nb, Ti			
1.4510	–	430Ti	–	0.05x	17	.	.	0.6 Ti	230-240	420-600	23
1.4511	–	430Nb	–	0.05x	17	.	.	0.6Nb	230-240	420-600	23
1.4512	409S19	409	–	0.03x	11	.	.	0.5 Ti	210-220	380-560	25
1.4521	–	(444)	–	0.025x	17	.	2	0.6 Ti			
1.4006	410S21	410	56A	.08-.15	12	.	.	.	400-450	550-850	12-20
1.4005	416S21	416	56AM	.08-.15	12	.	.	.35xS	450	650-850	12
1.4021	420S29	420	56B	.16-.25	12	.	.	.	450-550	650-950	10-15
1.4028	420S45	420	56D	.26-.35	12	.	.	.	600	740-1000	10-15
1.4029	416S37	416	56CM	.25-.32	12	.	.	.35xS			
1.4057	431S29	431	57	.12-.22	15	2	.	.			
1.4104	416S29	416	56BM	.10-.17	16	.	0.4	.35xS	500	650-850	10
1.4112	–	440B	–	.85-.95	17	.	1.0	0.1V		900 max	12
1.4125	–	440C	–	.95-1.2	17	.	0.6	.		900 max	12
1.4594	460S52	–	–	0.7x	14	5	1.5	1.5Cu	700-1000	930-1270	10
1.4749	–	446	–	.15-.20	26	.	.	0.2N			
1.4301	304S31	304	58E	0.07x	18	8	.	.	210-260	520-750	45
1.4303	305S19	305	–	0.06x	18	11	.	.	200-250	500-650	45
1.4305	303S31	303	58M	0.10x	18	8	.	0.35xS	190-230	500-700	35
1.4306	–	304L	–	0.030x	18	10	.	.	200-250	500-670	45
1.4307	304S11	304L	–	0.030x	18	8	.	.	200-250	500-670	45
1.4310	301S21	301	–	0.05/0.1	517	6	.	.	250-280	600-950	40
1.4311	304S61	304LN	–	0.030x	18	9	.	0.22xN	270-320	550-750	40
1.4372	–	201	–	0.15x	17	4.5	.	6.5Mn	330-380	750-950	40
1.4401	316S31	316	58J	0.07x	17	11	2	.	220-270	520-680	40
1.4404	316S11	316L	–	0.030x	17	11	2	.	220-270	520-680	40
1.4406	316S61	316LN	–	0.030x	17	11	2	0.22xN	280-330	580-780	40
1.4432	316S13	316L	–	0.030x	17	11	2.5	.	220-270	520-700	40
1.4435	316S13	316L	–	0.030x	17	13	2.5	.	220-270	520-700	40
1.4436	316S33	316	58J	0.05	17	11	2.5	.	220-270	500-730	40
1.4438	317S12	317L	–	0.030x	18	13	3	.	220-270	520-720	35
1.4439	–	–	–	0.030x	17	13	4	0.22xN	270-320	580-780	35
1.4541	321S31	321	58B	0.08x	18	9	.	0.5Ti	200-250	500-720	40
1.4550	347S31	347	58F	0.08x	18	9	.	0.5Nb	200-250	500-720	40
1.4571	320S31	(316Ti)	–	0.08x	17	11	2	0.5Ti	220-270	520-690	40
1.4833	309S16	309	–	0.15x	22	12	.	.			
1.4845	310S24	310	–	0.10x	25	20	.	.			
1.4878	321S51	321H	–	0.10x	18	9	.	0.6Ti			



*Amari is a registered trademark of Amari Metals Ltd*

© Copyright: Amari Metals Ltd, 25 High Street, Cobham, Surrey, KT11 3DH

All Data is indicative only and must not be seen as a substitute for the full specification from which it is drawn. In particular, the mechanical property requirements vary widely with temper, product form and product dimensions. For more complete details please refer to the relevant specification.

# Stainless Steel – EN Standards for Cold Rolled

*This information is based on our present knowledge and is given in good faith. However, no liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon. As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose. Any advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. Any contract between the Company and a customer will be subject to the Company's Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.*



**Amari is a registered trademark of Amari Metals Ltd**

© Copyright: Amari Metals Ltd, 25 High Street, Cobham, Surrey, KT11 3DH

All Data is indicative only and must not be seen as a substitute for the full specification from which it is drawn. In particular, the mechanical property requirements vary widely with temper, product form and product dimensions. For more complete details please refer to the relevant specification.