

Duplex Stainless Steel

Duplex stainless steels are extremely corrosion resistant, work hardenable alloys. Their microstructures consist of a mixture of austenite and ferrite phases. As a result, duplex stainless steels display properties characteristic of both austenitic and ferritic stainless steels. This combination of properties can mean some compromise when compared with pure austenitic and pure ferritic grades.

Duplex stainless steels are, in most cases, tougher than ferritic stainless steels. Strengths of duplex stainless steels can in some cases be double that for austenitic stainless steels.

Whilst duplex stainless steels are considered resistant to stress corrosion cracking, they are not as resistant to this form of attack as ferritic stainless steels. However, the corrosion resistance of the least resistant duplex stainless steels is greater than that for the most commonly used grades of stainless steels, i.e. 304 and 316.

Duplex steels are also magnetic, a property that can be used to easily differentiate them from common austenitic grades of stainless.

Property data given in this document is typical for flat rolled products covered by ASTM A240/A240M. ASTM, EN or other standards may cover products sold by Cashmores. It is reasonable to expect specifications in these standards to be similar but not necessarily identical to those given in this datasheet.

Applications

Duplex stainless steels are typically used in:

- ◆ Chemical processing, transport and storage
- ◆ Oil and gas exploration and offshore rigs
- ◆ Oil and gas refining
- ◆ Marine environments
- ◆ Pollution control equipment
- ◆ Pulp & paper manufacturing
- ◆ Chemical process plant

Alloy Designations

Due to excellent corrosion resistance and high strength, the most widely used duplex stainless steel is 2205. The name 2205 comes from a typical composition of 22% Chromium and 5% Nickel. Other designations for 2205 are given in the table below.

There are many other duplex stainless steels most of which are proprietary grades developed and produced by individual manufacturers. One example is LDX2101 from Outokumpu.

Euronorm	UNS	BS	En	Grade
1.4462	S31803 S32205	318S13	-	2205
1.4507	S32520 S32550	-	-	
		-	-	LDX2101



Amari is a registered trademark of Amari Metals Ltd

© Copyright: Amari Metals Ltd, 25 High Street, Cobham, Surrey, KT11 3DH

All Data is indicative only and must not be seen as a substitute for the full specification from which it is drawn. In particular, the mechanical property requirements vary widely with temper, product form and product dimensions. For more complete details please refer to the relevant specification.

Typical Chemical Composition

%	2205	1.4507	LDX2101
C	0.03 max	0.03 max	0.03 max
Mn	2.0	1.5	
Si	1.0	0.8	
P	0.03	0.035	
S	0.02	0.02	
Cr	21-23	24-26	21.5
Mo	2.5-3.5	3.0-5.0	0.3
Ni	4.5-6.5	5.5-8.0	1.5
N	0.08-0.2	0.2-0.35	0.22
Cu	-	0.5-3.0	

Typical Mechanical Properties

Grade	2205	1.4507	LDX2101
Tensile Strength (MPa)	620	770	650-700
Proof Stress 0.2% (MPa)	450	550	450-530
Elongation A5 (%)	25	25	30
Hardness Rockwell C	31	-	-


Typical Physical Properties

Property	2205	1.4507
Density (g.cm ³)	7.805	7.810
Modulus of Elasticity (GPa)	200	205
Electrical Resistivity (Ω.m)	0.085x10 ⁻⁶	0.085x10 ⁻⁶
Thermal Conductivity (W/m.K)	19 at 100°C	17 at 100°C
Thermal Expansion (m/m.K)	13.7x10 ⁻⁶ to 100°C	13.5x10 ⁻⁶ to 200°C

Corrosion Resistance

Duplex stainless steels are extremely corrosion resistant. They have high resistance to intergranular corrosion. Even in chloride and sulphide environments, duplex stainless steels exhibit very high resistance to stress corrosion cracking.

The super duplex grades are even more resistant to corrosion.

	<p><i>Amari is a registered trademark of Amari Metals Ltd</i></p> <p>© Copyright: Amari Metals Ltd, 25 High Street, Cobham, Surrey, KT11 3DH</p>
<p>All Data is indicative only and must not be seen as a substitute for the full specification from which it is drawn. In particular, the mechanical property requirements vary widely with temper, product form and product dimensions. For more complete details please refer to the relevant specification.</p>	

Heat Resistance

The high chromium content of duplex stainless steels that protects against corrosion, causes embrittlement at temperatures over about 300°C.

At low temperatures duplex stainless steels have better ductility than the ferritic and martensitic grades. Duplex grades can readily be used down to at least -50°C.

Fabrication

Fabrication of all stainless steels should be done only with tools dedicated to stainless steel materials. Tooling and work surfaces must be thoroughly cleaned before use. These precautions are necessary to avoid cross contamination of stainless steel by easily corroded metals that may discolour the surface of the fabricated product.

Heat Treatment

Duplex stainless steels cannot be hardened by heat treatment. They can however be work hardened.

Solution treatment or annealing can be done by rapid cooling after heating to around 1100°C.

Machinability

Although machinable, the high strengths of duplex stainless steels makes machining difficult. As an example, machining of 2205 is around 20% slower than for 304.

Machining can be enhanced by using the following rules:

- ◆ Cutting edges must be kept sharp. Dull edges cause excess work hardening.
- ◆ Cuts should be light but deep enough to prevent work hardening by riding on the surface of the material.
- ◆ Chip breakers should be employed to assist in ensuring swarf remains clear of the work
- ◆ Low thermal conductivity of austenitic alloys results in heat concentrating at the cutting edges. This means coolants and lubricants are necessary and must be used in large quantities.

Welding

Duplex stainless steels have good weldability. All standard welding processes can be used. They are not quite as easily welded as the austenitic grades but low thermal expansion in duplex grades reduces distortion and residual stresses after welding. The recommended filler material for 2205 stainless steel is 2209.

This information is based on our present knowledge and is given in good faith. However, no liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon. As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose. Any advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. Any contract between the Company and a customer will be subject to the Company's Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.

