Aluminium Alloy G.AL C250 Precision Milled Plate



SPECIFICATIONS

Commercial	5083
------------	------

G.AL C250 Precision Milled Plate, Alloy 5083 is supplied homogenised and stress relieved in thicknesses from 5mm to 100 mm

It is precision milled to a roughness \mbox{Ra} of 0.4 microns and supplied folied on both sides.

CHEMICAL COMPOSITION

G.AL C250 Alloy 5083 Precision Milled Plate		
Element	% Present	
Magnesium (Mg)	4.00 - 4.90	
Manganese (Mn)	0.40 - 1.00	
Iron (Fe)	0.40 max	
Silicon (Si)	0.0 - 0.40	
Titanium (Ti)	0.05 - 0.25	
Chromium (Cr)	0.05 - 0.25	
Copper (Cu)	0.10 max	
Others (Total)	0.0 - 0.15	
Zinc (Zn)	0.0 - 0.10	
Other (Each)	0.0 - 0.05	
Aluminium (AI)	Balance	

SUPPLIED FORMS

Plate

GENERIC PHYSICAL PROPERTIES

Property	Value	
Density	2.66 g/cm³	
Melting Point	570 °C	
Thermal Expansion	23.3 x10 ⁻⁶ /K	
Modulus of Elasticity	70 GPa	
Thermal Conductivity	110-130 W/m.K	
Electrical Resistivity	29-32 % IACS	
Heat Capacity	900 J/kgK	

MECHANICAL PROPERTIES

G.AL C250 Alloy 5083 G.AL C250 Alloy 5083		
Property	Value	
Proof Stress	110-130 MPa	
Tensile Strength	230-260 MPa	
Hardness Brinell	68-73 HB	
Elongation A	10-15 %	

TOLERANCES

Thickess (mm)	Flatness Tol (mm)	Thickness Tol (mm)	Width & Length Tol (mm)
5	0.80	+/- 0.1	-0 / +20
6-12.7	0.40	+/- 0.1	-0 / +20
Over 12.7	0.13	+/- 0.1	-0 / +20

Aluminium Alloy G.AL C250 Precision Milled Plate



CONTACT

Please make contact directly with your local service centre, which can be found via the Locations page of our web site. Address:

Web: www.amari-ireland.com

REVISION HISTORY

Datasheet Updated 16 February 2023

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's $% \left(1\right) =\left(1\right) \left(1\right) \left$ assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.